

ISO 9001:2015
No.: 92200062



ISO 14001:2015
No.: 142200063



ISO 45001:2018
No.: 452200064

DESCRIPTION

Gboard[®] Deciloc is a complete sound barrier. Due to its high density and high fiber content, when installed in a partition system, ceiling or dry lining system, sound transmission from one area to another is practically eliminated.

Gboard[®] Deciloc STC rating is designed to reach a sound attenuation up to 75 dB within the system.

Gboard[®] Deciloc is used in loud spaces to eliminate sound transmission to neighboring areas. It can be installed around generators and technical rooms, office spaces, hospitals, meeting rooms, cinemas, theaters and large commercial areas where separation is needed.

APPLICATIONS

- Around generator and technical rooms
- Office spaces
- Hospitals
- Cinemas
- Theaters

FEATURES

- Easy and dry installation
- Superior sound damping
- High rated STC wall assemblies



Sound block



Advanced impact
resistance






No
cracking



Eco-friendly

PROPERTIES

SURFACE FINISHING	EDGE TYPES	STANDARDS	DIMENSIONS
Painted (water or oil base paint)	Squared edge 	ASTM C 1396	Width 1200mm 1220mm
Cladding (wallpaper, vinyl, wood...)	Tapered edge 	ASTM C 518	Length 2000mm, 2400mm, 2440mm, 2500mm, 3000mm
Joint filling with Gcoat [™] All Purpose Joint Compound	Beveled edge 	ASTM C 473	Thicknesses 8.0mm, 9.5mm 12.5mm, 15mm, 15.9mm, 18mm

*Varying dimensions available upon request

PHYSICAL SPECIFICATIONS

SPECIFICATIONS	UNIT	VALUE	STANDARD
Thickness	mm	12.5	ASTM C 1396
Density	Kg/m ³	870.2	ASTM C 1396
Weight per unit area	Kg/m ²	10.71	ASTM C 1396
Tolerance of length	mm	2402	ASTM C 1396
Tolerance of width	mm	1200	ASTM C 1396
Tolerance of thickness	mm	12.5	ASTM C 1396
Depth of taper	mm	1.24	ASTM C 1396
Width of taper	mm	42.3	ASTM C 1396
Squareness of edges	mm	1.4	ASTM C 1396
Core hardness	N	321	ASTM C 1396
Edge hardness	N	298	ASTM C 1396
End hardness	N	308	ASTM C 1396
Flexural breaking load long edge	N	536	ASTM C 1396
Flexural breaking load short edge	N	249	ASTM C 1396
Nail pull strength	N	377	ASTM C 1396
Bending radius	mm	1890	ASTM C 1396
Humidified deflection	mm	1.7	ASTM C 1396
Thermal conductivity	W/m.k	0.1799	ASTM C 518

RECOMMENDATION

- Cutting and scoring happen from the front face side of the board.
- Use phosphate self-tapping screws with a metal frame lower than 0.7 mm for board fixing.
- Use phosphate self-drilling screws with a metal frame greater than 0.7 mm for board fixing.
- Vertical screw spacing for the first layer of gypsum is 25cm, 50cm for the second, and 75cm for the third.

STORAGE AND HANDLING

- Avoid contact with moisture or temperatures higher than 50°C for prolonged periods of time.
- Store in a dry/ventilated area above ground level (not in direct contact with the ground).
- Cover boards with plastic sheets.
- Avoid direct rain or sunlight.
- Avoid cracking or damaging the boards during installation.

The information herein and recommendations set forth are presented in good faith and believed to be correct as of the date hereof, ASK Gypsum Factory Ltd., and its affiliated, and sister companies do not make representations or warranties as to the completeness or accuracy thereof. Information is supplied upon the condition that the persons receiving the same will make their own determination as to its suitability for their purpose prior to use. In no event will ASK Gypsum Factory Ltd. and its affiliated and sister companies be responsible for indirect, consequential, or incidental damages arising out of the use of, or inability to use this product. Our liability, if any, shall be capped to the price of the product purchased.

All specifications reflect averages derived from product sample testing and are provided as guidance only. They are subject to inherent variances and may be changed without notice to improve reliability, function, or design or otherwise.

Manufactured according to ASTM & EN standards by ASK Gypsum Factory Ltd.