



ISO 9001:2015
No.: 92200062



ISO 14001:2015
No.: 142200063



ISO 45001:2018
No.: 452200064

DESCRIPTION

GULF Gypsum Fibra is suitable for surface finishings and decorative elements, with a fast-setting time. It is made of extremely fine white gypsum, consisting essentially of calcined gypsum $\text{CaSO}_4 \cdot 2\text{H}_2\text{O}$.

FEATURES

- Durable
- High whiteness
- Decorative
- High flexural and compressive strength
- No cracks

APPLICATIONS

- Surface finishing
- Decorative elements and casting
- Suspended ceilings
- Concealing and filling processes
- Marble bonding
- Decorative workshops
- Repairing cracks



Durable



Highly
flexural



High
Compressive
strength



No
cracking

METHOD OF USE

- Clean and clear the container from remnants of previous mixtures to prepare the mortar. The water used in the mixture should not be salty, acidic, or oily. The water temperature must be between 17 and 23°C.
- Pour water into the container and then add GULF Gypsum Fibra. Give the plaster 3 to 4 mins to absorb the water.
- Mix GULF Gypsum Fibra using a trowel or a hand mixer until a homogeneous flowing consistency is reached. If a hand mixer is used, operate it at low speed since it can affect the setting time.
- Do not add water or extra plaster to the mortar during or after mixing to prevent lumps.
- Do not mix any other product or materials into GULF Gypsum Fibra.
- Clean the mold of the mortar and place it on a surface enabling to vibrate the mold easily.

- Lubricate the mold surface using an appropriate lubricant to ensure smooth removal of the plaster from the mold.
- Pour the mortar into the mold and covering it completely.
- Clean the surroundings of the mold when the plaster begins to set. The plaster in the mold will begin to warm. After the warming period, the plaster is unmolded.
- Keep the unmolded plaster in the ambient temperature until it dries out. This will prevent breakage and cracks during installation.
- Prepare the mortar that bonds the mold using GULF Gypsum Fibra in the same way.

TECHNICAL SPECIFICATIONS

SPECIFICATIONS	UNIT	VALUE	STANDARD
Water/gypsum ratio (water consistency)	%	70	ASTM C 472
Physical state	-	Powder	Visual inspection
Appearance	-	White fine powder	Spectrophotometer
Initial setting time	min	6 - 8	ASTM C 472
Final setting time	min	17 - 20	ASTM C 472
Fineness on 150 μ sieve	%	>= 95	ASTM C 472
Fineness on 250 μ sieve	%	100	ASTM C 472
Fineness on 600 μ sieve	%	100	ASTM C 472
Combined water at 230 °C	%	5 - 6	ASTM C 471
Compressive strength	MPa (N/mm ²)	>= 12	ASTM C 472
Flexural strength	N/mm ²	>= 4	EN 13279
Insoluble residue + silica dioxide	%	<= 0.17	ASTM C 471
Sodium chloride NaCl	-	NA	ASTM C 471
Calcium oxide CaO	%	>= 31	ASTM C 471
Sulfur trioxide SO ₃	%	>= 40	ASTM C 471

RECOMMENDATION

It is recommended to use safety gloves, masks and glasses when applying the product to prevent the risks of inhalation and irritation of the skin and eyes.

STORAGE AND HANDLING

- The properties of the product are guaranteed only if it is stored and used in the right way.
- If the product becomes moist, hardened lumps that deteriorate its properties will develop.
- Store in a dry area.
- Avoid the bag's contact with the ground to protect it against humidity.

The information herein and recommendations set forth are presented in good faith and believed to be correct as of the date hereof, ASK Gypsum Factory Ltd., and its affiliated, and sister companies do not make representations or warranties as to the completeness or accuracy thereof. Information is supplied upon the condition that the persons receiving the same will make their own determination as to its suitability for their purpose prior to use. In no event will ASK Gypsum Factory Ltd. and its affiliated and sister companies be responsible for indirect, consequential, or incidental damages arising out of the use of, or inability to use this product. Our liability, if any, shall be capped to the price of the product purchased.

All specifications reflect averages derived from product sample testing and are provided as guidance only. They are subject to inherent variances and may be changed without notice to improve reliability, function, or design or otherwise.

Manufactured according to ASTM & EN standards by ASK Gypsum Factory Ltd.